



WARREN
ENVIRONMENTAL

301-FA
FAST ACTIVATING

DESCRIPTION: A two part, highly thixotropic epoxy system formulated for spraying with Warren Environmental, Inc.'s patented meter/mix spray equipment.

CHARACTERISTICS: This system uses a fast Activator to speed up cure in cold weather. Formulated with special additives and modifiers to enhance the water resistance, chemical resistance, and bond strength to a variety of substrates as well as its own internal strength. The high thixotropic index allows for up to a ¼" build-up on vertical surfaces without sag.

APPLICATION: Designed for use with Warren Environmental's patented meter, mix and spray equipment. The epoxy component utilizes a 2 parts base to 1 part activator mix ratio by volume. This product is sold and installed only by technicians specifically trained and licensed in our patented techniques.

ADVANTAGES:

- % Cold weather application
- % Long Open time for Efficient Topcoating
- % Excellent Cure at Low Temperature
- % Excellent Cure at High Humidity
- % Zero Induction Time
- % 0% VOC's
- % 100% Solids
- % Long Working Time Relative to Cure Time
- % Ready-to-Use (No Thinning Required)
- % Excellent Water and Chemical resistance with ambient cure
- % Achieve high-build thicknesses without sag

CERTIFICATION:

None

SPECIAL SAFETY AND HANDLING: There are no special safety or handling procedures beyond those published on the reverse and the Material Safety Data Sheets.

Typical Properties

Liquid Properties (Systems)

Viscosity	90,000-120,000 cps
Thixotropic Index	5.0-6.0
Specific Gravity	1.143
Flash Point (Closed Cup)	>235°F
Color	Varies
Geltime (200g@77°F)	27 minutes
Thin Film Set (@ 77°F)	2 hours
Thin Film Set (@ 40°F)	8 hours

Physical Properties

(1/8" Casting)

Tensile Strength (ASTM D638-86)	7000 psi
Flexural Strength (ASTM D790-86)	10,000 psi
Flexural Modulus @ 0.100" (ASTM D790-86)	450,000 psi
Compressive Strength (ASTM D695-85)	10,000 psi
Glass Transition Temperature (ASTM D3418-82)	151°F
Tensile Elongation @ Break	4.8%
Thin Film Set (@77°F)	2 hours
Shore D Hardness	83-85

Chemical Resistance

(28 Day Immersion)

Chemical	Weight Gain (%)
Toluene	0.99
Ethanol	4.68
10% Acetic Acid	3.85
70% Sulfuric Acid	0.13
50% Sodium Hydroxide	0.09
Distilled Water	1.11
Methanol	9.55
Xylene	0.69
Butyl Cellosolve	1.18
Methyl Ethyl Ketone	11.19
10% Lactic Acid	3.24
Bleach	0.93
1,1,1 Trichloroethane	0.43
10% Nitric Acid	2.05
30% Nitric Acid	4.17

Contact us at:

PO Box 1206, Carver, MA 02330
www.warrenenviro.com

Tel. (508) 947-8539

Fax (508) 947-3220
E-mail: info@warrenenviro.com

All values reported above are typical values, and are reported as a means of reference. Individual testing should be done to determine actual results, tested at specific conditions.